This is a pre- or post-print of an article published in
Dandekar, P., Jain, R., Keil, M., Loretz, B., Muijs, L.,
Schneider, M., Auerbach, D., Jung, G., Lehr, C.-M., Wenz,
G.

Cellular delivery of polynucleotides by cationic
cyclodextrin polyrotaxanes
(2012) Journal of Controlled Release, 164 (3), pp. 387-
393.

Cellular Delivery of Polynucleotides by Cationic Cyclodextrin Polyrotaxanes

Prajakta Dandekar^{a§}, Ratnesh Jain^{a§}, Manuel Keil^b, Brigitta Loretz^a, Leon Muijs^a, Marc Schneider^c, Dagmar Auerbach^d, Gregor Jung^d, Claus-Michael Lehr^{a**}, Gerhard Wenz^{b*}

^aDepartment of Drug Delivery (DDEL), Helmholtz-Institute for Pharmaceutical Research Saarland (HIPS), Helmholtz-Center for Infection Research (HZI), Saarland University, D-66123 Saarbrücken, Germany.

^bOrganic Macromolecular Chemistry, Campus C4 2, Saarland University, D-66123 Saarbrücken, Germany.

^cPharmaceutical Nanotechnology, Campus A4 1, Saarland University, D-66123 Saarbrücken, Germany.

^dBiophysical Chemistry, Campus B2 2, Saarland University, D-66123 Saarbrücken, Germany.

[§]These authors contributed equally to this work

*Corresponding author, Tel.: +49 681 302 3449, fax: +49 681 302 3909, E-mail: g.wenz@mx.uni-saarland.de

**Corresponding author, Tel.: +49 681 302 3039; fax: +49 681 302 4677, E-mail: lehr@mx.uni-saarland.de

Abstract

Cationic polyrotaxanes, obtained by temperature activated threading of cationic cyclodextrin derivatives onto water soluble cationic polymers (ionenes), form metastable nanometric polyplexes with pDNA and combinations of siRNA with pDNA. Because of their low toxicity, the polyrotaxane polyplexes constitute a very interesting

system for the transfection of polynucleotides into mammalian cells. The complexation of Cy3-labeled siRNA within the polyplexes was demonstrated by fluorescence correlation spectroscopy. The uptake of the polyplexes (red) was imaged by confocal fluorescence microscopy using the A549 cell line as a model (blue: nuclei, green: membranes). The results prove the potential of polyrotaxanes for further investigations involving knocking down genes of therapeutic interest.

Keywords: siRNA, pDNA, polyrotaxane, polyplex, transfection, fluorescence.

1. Introduction

Therapeutic applications of pDNA (plasmid DNA) as well as siRNA (small interfering RNA) are largely hampered by the low transfection efficiencies and severe toxicities of most of the commonly employed viral and non-viral carriers. Therapeutic applications of viral vectors based on first generation adenoviral vectors has encountered difficulties due to their known ability to induce massive immune reactions [1, 2]. Alternatively, non-viral synthetic vectors, though generally non-immunogenic, show lower transfection efficiencies and significant cytotoxicity at high or repetitive doses. Among them polycationic polymers based on polyethylene imine (PEI) [3], dendrimers [4], chitosan derivatives [5, 6] and polylysine [7] form

nanometric complexes (polyplexes) with pDNA and siRNA have already demonstrated to enhance the uptake of the associated nucleotides [4]. But despite their ability to enhance the cellular uptake of condensed siRNA, they still exhibit low knockdown efficiency due to insufficient siRNA release [8]. Recently, high knockdown efficiency was indeed reported for branched polyaminoamides, but the employed solid-phase synthesis is difficult to scale up [9]. Commercial transfection agents based either on cationic polymers, cationic lipids, cationic peptides or their combinations show high transfections efficiencies and low toxicities in cellular investigations *in vitro*; but manufacturers usually discourage their application *in vivo*, as the observed transfection is usually paralleled by some noticeable cytotoxicity. Furthermore, bioreducibility of transfection agents is essential for the release of the complexed nucleotides inside the cells with subsequent elimination of the degradation products [10]. Amongst several transfection agents explored in clinical studies so far [11, 12], the supramolecular cationic cyclodextrin polymers have also yielded appreciable results [13].

A good transfection agent should form compact weakly cationic polyplexes with pDNA or siRNA, having sizes $d \leq 200$ nm to enable their efficient cellular uptake by endocytosis. Shielding of cationic charge of transfection agents by inert hydrophilic polymers such as polyethylene glycol (PEG) leads to a reduction of their toxicity [14], and protects polynucleic acids from degradation in the acidic milieu of the endosomes or lysosomes [15]. Furthermore the degradation products of the carrier should be sufficiently small (molecular weight < 20 kDa) to enable rapid removal by excretory organs like kidneys. In a successful system, reported by M. Davis et al., PEG side chains were mounted on to a polycationic backbone via supramolecular cyclodextrin-adamantane interactions, which are stable only for a limited period of time sufficient for delivery of siRNA [13, 16].

Cyclodextrins (CDs), cyclic oligomers consisting of 6, 7, or 8 glucose units (α -, β -, γ CD), and CD derivatives have already been commercially exploited for enhancing the delivery of sparingly water soluble drugs such as prostaglandins [17], or piroxicam [18], and other non steroidal anti-inflammatory drugs [19]. CDs are amenable for regioselective or statistical modifications at the hydroxyl groups or the primary carbon atoms (C-6), respectively. The resulting CD derivatives, such as hydroxypropyl- β CD, often show higher solubility in water and lower toxicity than the corresponding native CDs [20]. Amino functionalities have been multivalently attached to CDs via thioether linkages at the primary positions leading to highly water-soluble CD derivatives, which show improved binding affinities and aqueous solubilities compared to native CDs [21-23]. CDs can complex not only monomeric guests but also polymeric ones. For example the smallest CD, α CD, threads onto PEG forming a water insoluble complex. Attachment of bulky groups (so called “stoppers”) at both ends of the PEG chain prevents the threaded CD rings from sliding off. The resulting “molecular necklace” [24] is referred to as a *polyrotaxane*. This name is derived from the terms ‘**rotation** and **axis**’, since the threaded CD rings retain their mobility around the PEG backbone. PEG-based polyrotaxanes have been further modified with cationic dimethylaminoethyl groups by a statistic approach [25]. The resulting cationic polyrotaxanes were found to deliver pDNA into 3T3 fibroblasts. Especially those cationic CD polyrotaxanes, in which stopper groups had been linked via bio-reducible disulfide bonds, were specifically effective for intracellular delivery of pDNA [25, 26].

We assembled CD polyrotaxanes using an ionene backbone, which were temporarily stable and did not require the attachment of terminal stoppers. An *ionene-n* is a cationic water-soluble polymer with repeat units consisting of a spacer with n methylene groups and a dimethylammonium group, shown in Figure 1. Ionenes are

only slowly complexed by α CD at elevated temperatures (70°C), due to steric hindrance from the bulky dimethylammonium groups. At lower temperatures, 25-37°C, they are stable for a limited period of time in aqueous solution (1 - 10 days) [27, 28].

Figure 1. Chemical structure of the ionenes and CDs used as building blocks for polyrotaxane synthesis.

Not only native CDs but also cationic CD derivatives can be threaded onto ionenes. This approach allowed the assembly of a polyrotaxane with many cationic side-groups from a well-defined molecular construction kit, as shown in Figure 2a. **PRx1** consisted of about 90 hexacationic αCD rings threaded onto the ionene-11 chain [29]. The molecular weight per nitrogen, $M/N = 250$ Da, was much higher than that of PEI ($M/N = 80$ Da for the hydrochloride). Already at $N/P = 2$ **PRx1** formed compact, spherical polyplexes with pDNA with small diameters $d < 100$ nm and exhibited higher rates of DNA transfection into various cells types than PEI accompanied with a lower toxicity than PEI. The lower toxicity of **PRx1** can be attributed to its lower cationic charge density compared to PEI. Transfection efficiency of luciferase pDNA into cancer cells (MCF7) was very high and similar to PEI, which was not surprising, because gene delivery into cancer cells is known to be easier than into normal

healthy cells. However, the transfection rate into human alveolar basal epithelia cells and mouse myoblasts with **PRx1** was 10-30 times higher than PEI [29]. This significant result may be attributed (a) to the rather flexible and mobile structure due to many rotational and translational degrees of freedom within **PRx1**, and (b) to the limited lifetime of **PRx1**, which facilitates release of the pDNA after intracellular transport.

Figure 2. Schematic drawing of polyrotaxanes **PRx1** and **PRx2** obtained by threading of cyclodextrins and cationic cyclodextrin derivatives onto ionenes, **PRx1** was from ionene-11 and hexacationic α CD derivative [29], **PRx2** was from heptacationic β CD, α CD and ionene-6,10, this contribution.

After demonstrating delivery of pDNA we focused on the delivery of siRNA, for its implications in the RNA interference (RNAi) therapy of diseases like cancer [8] and tuberculosis etc. [30]. Furthermore, we synthesized a more labile polyrotaxane, **PRx2**, by subsequent threading of heptacationic β CD rings and native α CD rings onto ionene-6,10, in which the α CDs acted as supramolecular stoppers. Threaded β CD rings would otherwise immediately dissociate from the ionene chain after dilution, because their internal diameter is significantly larger than the one of α CD.

The even higher mobility of the threaded heptacationic β CD rings was expected to further improve transfection efficiency.

2. Materials and methods

2.1. Materials

α CD and β CD (Wacker-Chemie GmbH, München, Germany, pharmaceutical grade, 99%) were dried for 16 h at 70°C under vacuum. Dulbecco's modified Eagle's medium (DMEM) and fetal calf serum (FCS) were purchased from GIBCO (Karlsruhe, Germany). Atto647N protein labeling kit was from Jena Bioscience (Jena, Germany). Fluorescein wheat germ agglutinin (FITC-WGA) was from Vector (Vector Laboratories, Inc., Burlingame, CA), 4',6-diamidino-2-phenylindole dihydrochloride (DAPI) was from Fluka Chemie GmbH (Buchs, Switzerland). All other chemicals including PEI (Mw 25,000 branched, Cat. No. 9002-98-6) were purchased from Sigma-Aldrich (Munich, Germany), unless otherwise stated.

Ionene-6,10 [31] and heptakis-[6-deoxy-(2-amino-ethylsulfanyl)]- β CD (**HAES β CD**) [21] were synthesized as described previously.

PRx2 was synthesized by stirring a solution of 51.4 mg (0.134 mmol) of ionene-6,10 and 483.6 mg (0.268 mmol) of **HAES β CD** in 5 mL 0.1 M NaCl for 8h at 25°C and subsequent addition of a solution of 514 mg α CD (0.528 mmol) in 5 mL water stirring for further 16 h at 70°C. After cooling to r.t. the solution was subjected to ultrafiltration over a cellulose membrane (UC010, cut-off 10 kDa, MICRODYN-NADIR GmbH, Wiesbaden, Germany). The retentate was lyophilized to furnish 93 mg (85 % based on ionene-6,10) of **PRx2**. ^1H NMR δ /ppm: 5.08 (1.35 H, **HAES β CD**), 5.02 (0.58 H, α CD), 3.79, 3.66, 3.44, 3.20, 3.05, 2.96, 2.83, 1.70 (8.0 H, methylene), 1.27-1.34 (16 H, methylene). Occupancies per polymer repeat unit: CD: 9 %; **HAES β CD**: 20 %.

PRx2-Atto647N was synthesized by mixing a solution of 10 mg **Prx2** (0.12 μmol polyrotaxane) in 1.45 mL 0.1 M NaHCO_3 with a solution of 10 μg (0.12 μmol) Atto647N-NHS-ester in 10 μL DMF and agitation by a shaker for 3 days at r.t. under exclusion of light. Afterwards the solution was subjected to ultrafiltration over a cellulose membrane (UC010, cut-off 10 kDa, MICRODYN-NADIR GmbH, Wiesbaden, Germany). The retentate was lyophilized to furnish 9.4 mg (94 %) of **PRx2-Atto647N**. The extinction at $\lambda = 641$ nm of an aqueous solution (0.47 mg mL^{-1} , 3.7 μM) was $E = 0.48$, which is equivalent to a degree of substitution of 0.95 per polyrotaxane chain, based on an extinction coefficient $\varepsilon = 1.37 \cdot 10^5 \text{ M}^{-1}\text{cm}^{-1}$ for Atto647N. Occupancies per polymer repeat unit: αCD : 9 %; **HAES β CD**: 20 %, Atto647N 0.6 %.

pDNA. pUC 18 plasmid DNA was obtained by transfection of E.coli XL-1 cells with pUC 18 for propagation and isolated using the QIAGEN Plasmid Mini Kit, Qiagen Inc., CA, USA.

siRNA. Cy3 labeled inactive siRNA (FACS Silencer® CyTM3 labeled negative control siRNA) was obtained from invitrogen (cat. No. AM4621). Luciferase specific siRNA duplex was purchased from Integrated DNA Technologies (IA, USA). The sequences for this siRNA are sense, 5'-GGUCCUGGAACAAUUGCUUUUACA-3' and anti-sense, 3'-UGUAAAAGCAAUUGUCCAGGAACCAG-5.'

Polyplexes were formulated by mixing same volumes of solutions of **PRx2** (3.6-29.4 $\mu\text{g mL}^{-1}$, depending on N/P) and of pDNA (8.25 $\mu\text{g mL}^{-1}$) and Cy3-siRNA (2.75 $\mu\text{g mL}^{-1}$) all in HEPES buffer (10 mM, pH 7.0, containing 5 wt.% glucose) at r.t. and shaking for 30 min. The N/P ratio is based on all nitrogens of **Prx2** including those of threaded CD-derivative and ionene backbone.

A549 cells type CCL-185 were purchased from ATCC, Manassas, VA, USA.

2.2. Methods

¹H NMR spectra were measured with an AVANCE 500 MHz spectrometer (Bruker BioSpin GmbH, Rheinstetten, Germany) and referenced to tetramethyl silane (0.00 ppm).

DLS. Characterization of polyplexes with respect to their average particle size, particle homogeneity (PI) and surface charge in terms of zeta potential was carried out using Zetasizer Nano-ZS (Malvern Instruments, Worcestershire, UK) equipped with a 4 mW He–Ne laser employing a wavelength of 633 nm and a backscattering angle of 173° at 25°C. All the samples were analyzed in triplicates after ensuring that their light scattering intensity was within the instrument's sensitivity range.

Fluorescence correlation spectroscopy was performed on a self-made setup [32]: The nanoparticles, i.e. the siRNA, were excited by a upconversion fiber laser operating at $\lambda=546$ nm (Guided Color Technologies). Focussing as well as fluorescence light collection was achieved by an objective lens (63x WI, NA 1.2, Zeiss). After passing a confocal pinhole with a diameter of 50 μm and a fluorescence filter (HQ 590/70, AHF Analysentechnik), the fluorescence photons were detected by a pair of avalanche photodiodes (SPCM-14-AQR, Perkin-Elmer Optoelectronics) and cross-correlated by a hard-ware correlator (Flex-02-D, correlator.com). The obtained autocorrelation traces were analyzed according to the two-dimensional diffusion model $g(\tau) = 1 + N^{-1}(1 + \tau / \tau_{\text{diff}})^{-1}$ for one particle and $g(\tau) = 1 + N_1^{-1}(1 + \tau / \tau_{\text{diff},1})^{-1} + N_2^{-1}(1 + \tau / \tau_{\text{diff},2})^{-1}$ for two diffusing particles [33]. The resulting diffusion dwell times t_{diff} are mean values from at least 4 repeated measurements. The hydrodynamic diameter was calculated using fluorescein as the reference with a hydrodynamic diameter of 1.6 nm [34].

FACS. Cells were seeded in a 24 well plate at a density of 50,000 cells per well in 1 mL of the growth medium. Once confluent, they were incubated with polyplexes (siRNA concentration 100 pmol/well) dispersed in Krebs-Ringer's solution (KRB; pH 7.4; 1 mL), for a period of 4 h. Afterwards, the polyplex solution was replaced by DMEM supplemented with FCS and the cells were incubated for further 18 h. The cells were then washed twice with PBS, were collected and centrifuged at 500×g and the resulting cell pellet was finally suspended in 500 µL of cell medium. A minimum of 10,000 individual cells per sample were analyzed using FACScan fluorescence-activated cell sorter (Becton-Dickinson, Heidelberg, Germany). The percentage of cell-associated fluorescence was determined using CellQuest software (Beckton-Dickinson, Heidelberg, Germany). All the experiments were conducted in triplicate.

Cell preparation for CLSM. Cellular uptake was conducted in presence of various inhibitors, namely 10 µg mL⁻¹ chlorpromazine (CHL), 10 µg mL⁻¹ nystatin (NYS) and 5 µg mL⁻¹ 5-(*N*-Ethyl-*N*-isopropyl)amiloride (EIPA). Cells were seeded in 24 well imaging plates FC, with Fluorocarbon Film Bottom (PAA Laboratories GmbH, Pasching, Austria), at a density of 50,000 cells per well, in 1 mL growth medium. Once confluent, they were incubated with the individual inhibitors in DMEM supplemented with FCS, for a period of 3 h. Afterwards, the cells were incubated with the polyplexes (siRNA concentration 100 pmoles/well) in KRB, along with the inhibitors, for further 4 h. Subsequently, the polyplex solution was replaced by inhibitor solutions in DMEM supplemented with FCS and the cells were incubated for further 18 h. The cells were washed twice with PBS, incubated for 15 min with 25 µg mL⁻¹ of FITC-WGA (emission: 515 nm, excitation: 495 nm) followed by two further washings with PBS and fixation with 4 wt. % paraformaldehyde in PBS for 10 min at room temperature. Once the cell membranes were stained fluorescent green by this dye, the cell nuclei were further stained with DAPI (emission: 461 nm,

excitation: 374 nm) by additional incubation with this dye for 15 min at r.t. Finally, the cells were washed twice with PBS and mounted in the fluorophor protector FluorSafe® reagent (Calbiochem, San Diego, CA, USA) and observed by CLSM.

CLSM. The imaging was performed employing a CLSM (LSM 510; Zeiss, Jena, Germany) equipped with an argon/neon laser and a 63x water immersion objective. Images were captured using three channels: 1. DAPI channel (excitation 360 nm, band pass filter 390-465 nm), 2. FITC-WGA channel (excitation 488nm, band pass filter 500-530 nm), 3. Cy3 channel (excitation 543 nm, band pass filter 560-615 nm). The location of nanoparticles with respect to the green cell membranes and blue nuclei was determined by acquiring 3D images using a stepper motor and image processing with the aid of Volocity® (Improvision, Tübingen, Germany) software. Images corresponding to a total of 100 cells were acquired for each inhibitor and quantification of number of cells positive for nanoparticle uptake (nanoparticles inside the cells) was carried out by a combined multiphoton-pixel analysis method reported by Labouta et al. [35].

Live cell imaging was performed using A549 cell monolayer cultures in RPMI-1640 with L-glutamine (PAA Laboratories GmbH, Pasching, Austria) supplemented with 10 % FBS (Gibco, Karlsruhe, Germany). The cells were plated in ibidi u-Slide 8 wellplate (80826, ibidi GmbH, Munich, Germany) at the density of 40,000 cells/well in 300 µL of growth medium. CellLight™ Early Endosomes-GFP was added for staining the endosomes as per the manufacturer's instructions. After 24 h, 50 µL of polyplexes formulated from Cy3-siRNA and **PRx2-Atto647N**, dispersed in KRB, were added to each well and the cells were subjected to live cell imaging for a time period of 4 h. For each time point, images were captured using three channels: 1. Endosomes-GFP channel (excitation 488 nm, band pass filter 500-550 nm), 2. Cy3 channel (excitation 543 nm, band pass filter 560-615 nm), 3. Atto647N channel

(excitation 633 nm, band pass filter 650-710 nm); image processing and analysis was conducted with LSM 510 software (Zeiss, Jena, Germany).

In vitro gene silencing efficacy of anti-Luc siRNA polyplexes was investigated in A549 cells. They were seeded in 24 well plates in a density of 50, 000 cells per well. After incubating overnight, the cells were transfected with pGL3-Control Vector (plasmid coding for luciferase gene) using jetPrime™, as per the manufacturer's protocol. The medium was replaced by medium without serum, containing pGL3 (1 µg per well + 2 µl jetPrime™ reagent) and incubated for a period of 3h. The medium containing pGL3 was then replaced by serum-free medium containing anti-Luc siRNA complexed polyplexes(100 pmol siRNA per well) and incubated for further 4h. Untreated cells, cells treated with naked siRNA and siRNA formulated with jetPrime™ reagent, with the same siRNA concentration in each case, were employed as controls during this study. The medium containing either formulated or non-formulated siRNA was then removed and the cells were incubated with normal growth medium, for a further period of 65 h (total time period for Luciferase expression = 72 h), with intermittent replacement of medium every 24 h. Luciferase gene expression was measured using Luciferase assay kit (Promega, WI, USA) and Tecan microplate reader (Tecan Deutschland GmbH, Crailsheim, Germany), as per the manufacturer's protocol. Protein concentration in the cell lysates was determined BCA assay as described by the manufacturer (Bicinchoninic Acid Kit for Protein Determination, Sigma, Cat. No. BCA1-1KT).The transfection experiments were conducted in triplicates and transfection efficiency was expressed as mean light units per mg of cell protein.

3. Results and discussion

Polyrotaxane **PRx2** was obtained by subsequent incubation of an aqueous solution of ionene-6,10 with the heptacationic β CD derivative, heptakis-[6-deoxy-(2-aminoethylsulfanyl)]- β CD, for 8 h at 25°C and for more 16 h at 70°C with α CD. Excess free α CD and β CD derivative was removed by ultrafiltration. Lyophilized polyrotaxane **PRx2** was white powder, which is stable for more than 6 months. The aqueous solution from **PRx2** has to be used within 3 d, because it slowly dissociates into its components. Solutions frozen at -20°C were stable. The amounts of threaded α CD und β CD derivative was determined from the integrals of the ^1H NMR signals of CD protons H-1 at 5.02 and 5.08 ppm, respectively, relative to the integral of the signal at 1.70 ppm of methylene protons (in β position to the nitrogens) of ionene-6,10. We found, that 9 % of the polymer repeats are covered by α CD and 20 % by the β CD derivative. As a control the amount of threaded α CD in **PRx2** was also estimated to 9 % from the known threading kinetics of α CD alone, assuming that the slow moving α CD rings push fast moving threaded β CD rings towards to the middle of the chain. This assumption should be valid as long as the coverage of the polymer chain is far from complete. Finally the structure of **PRx2** could be described by the following:

- one ionene-6,10 molecule consisted of ~150 repeat units, contour length 300 nm [31].
- 30 of the repeat units (20 %) are complexed by the cationic β CD derivative,
- 13 of the repeat units (9 %) are covered by α CD located at the chain ends,
- total molecular weight is ~125 kDa, molecular weight per nitrogen of **PRx2** is $M/N = 243$ Da.

Polyplexes obtained by complexing **PRx2** with plasmid DNA (pDNA) and siRNA (3:1 w/w) were obtained simply by mixing aqueous solutions of both components under

vigorous stirring. Generally no precipitate was formed. The slightly turbid polyplex dispersions were characterized by dynamic light scattering and zeta potential measurements and these results have been shown in Figure 3. The obtained particle sizes ranged from 140 to 220 nm depending on the N/P ratio (calculated from M/N of polyrotaxane where all nitrogens of threaded CD-derivative and ionene backbone were included). The smallest particles with $d = 140$ nm and with lowest polydispersity index $PDI = 0.14$ were found for $N/P = 2$. The zeta potential switched from negative to positive at an N/P between 1 and 2. For further investigations cationic nanoparticles with $N/P = 2$ and anionic ones with $N/P = 1$ were used. AFM investigations revealed a nearly spherical structure of the nanoparticles (shown in Supplement).

Figure 3. Particle sizes, polydispersities and zeta-potentials of the polyplexes of pDNA/siRNA 3:1 wt./wt. with **PRx2** at various N/P ratios.

Contrarily, siRNA alone did not form stable polyplexes with **PRx2**, because of its short, rigid structure (25 nucleotides) leading to weak Coulomb interactions between

polyanions and polycations. Therefore, siRNA was mixed with pDNA at 1:3 wt./wt. This mixture gave rise to stable polyplexes.

The Cy3-siRNA loaded polyplexes were analysed by fluorescence correlation spectroscopy of a diluted sample. The autocorrelation curve was fitted by using 2 diffusing particles corresponding to diffusion times $t_{\text{diff},1} = 0.33 \pm 0.15$ ms and $t_{\text{diff},2} = 6.35 \pm 1.6$ ms respectively. Stokes diameter d_s were derived from the diffusion times after calibration with fluorescein. The short time (0.33 msec) equivalent to $d_s = 6.7 \pm 3.0$ nm was attributed to free siRNA supported by control measurements with sole siRNA, while the long one (6.35 ms) equivalent to $d_s = 127 \pm 30$ nm was due to siRNA complexed within the nanoparticle. This particle size determined by fluorescence correlation spectroscopy agreed within the experimental error with the particle size $d = 140$ nm determined by dynamic light scattering. At $N/P = 2$ a major part of siRNA was bound, at $N/P = 10$ siRNA was bound completely.

Figure 4: Fluorescence correlation spectroscopy of nanoparticles derived from Cy3-siRNA, pDNA and **PRx2** $N/P = 2$, excitation at 546 nm, emission 570-590 nm.

The interaction of the **PRx2**-siRNA nanoparticles with the alveolar epithelial cell line A549 was investigated by fluorescence methods. Toxicities of the employed polyplexes were very low, much lower than those of PEI, as already observed for

PRx1 [29]. The uptake of the **PRx2**-siRNA nanoparticles in these cells was quantified by fluorescence activated cell sorting (FACS) considering the emission of Cy3 attached to siRNA, shown in Figure 5. Most of the A549 cells reach a fluorescence intensity, which is about tenfold than the one of the original cells. The uptake of non-complexed siRNA into these cells was found to be much lower. Further comparison of Mean Fluorescence Intensity (MFI) peaks of the polyplexes with $N/P = 1$ and $N/P = 2$ clearly revealed 36.3 ± 1.2 % for polyplexes with $N/P = 2$ versus 26.6 ± 0.34 for polyplexes with $N/P = 1$, indicating higher uptake of the former cationic particles.

Figure 5. FACS analysis A549 cells: original cells —, cells treated with Cy3-siRNA —, same with polyplexes of **PRx2** with Cy3-siRNA, $N/P = 1$ —, $N/P = 2$ —.

The cellular uptake of the **PRx2**-siRNA nanoparticles was further studied by confocal fluorescence microscopy to distinguish between nanoparticles attached to the cellular membrane and those distinctly uptaken into the cells. The detailed uptake mechanism of the polyplexes was evaluated using specific inhibitors of various endocytic pathways. *Chlorpromazine*, CHL, inhibits clathrin-mediated endocytosis through loss of clathrin and the adaptor protein, AP2, from the cell surface and their artificial assembly on endosomal membranes. *Nystatin*, NYS, the polyene antibiotic, acts as a selective inhibitor of caveolin mediated endocytosis due to its ability to interact with the cholesterol rich domains in the cell membrane and alter their properties. This inhibitory agent sequesters cholesterol from cell membrane, by forming large aggregates within the membrane, and thereby results in aberration of

caveolar structure and function, these being cholesterol-rich membrane domains. Finally, 5-(*N*-ethyl-*N*-isopropyl)amiloride (EIPA) has been reported to block macropinocytosis and phagocytosis by inhibiting the Na^+/H^+ exchange required for both these endocytic mechanisms [36].

The CLSM images (shown in Figure 6) showed distinct intracellular localization of polyplexes (red spots) with respect to the green cell membranes and blue nuclei, when the polyplexes ($\text{N/P} = 2$) were incubated in presence of CHL and NYS, thus precluding clathrin or caveolin mediated endocytosis appear to play a minor role as possible uptake mechanisms for the polyplexes. In case of EIPA, however, the polyplexes remained outside the cells, suggesting the involvement of macropinocytosis and phagocytosis in the cellular uptake of our polyplexes despite of their small size. This finding was in contrast to previous results where polyplexes of cationic carriers (100-200 nm) were taken up by receptor mediated endocytosis [37]. One explanation for this discrepancy might be that the polyplexes employed herein were quite soft, demonstrated by the collapse of their vertical height during AFM sample preparation (described in the Supplement). Such soft polyplexes might better adapt to the thermal fluctuations of the cell membrane during adsorption and internalization. Similar influence of mechanical properties of hydrogel nanoparticles on the pathway of their cellular uptake has been reported earlier for RAW 264.7 cells [38].

CHL

NYS

EIPA

Figure 6. Uptake of **PRx2** polyplexes ($N/P = 2$) into A549 cells after 25 h in presence of chlorpromazine (CHL), nystatin (NYS), and 5-(*N*-ethyl-*N*-isopropyl)amiloride (EIPA), green: cell membranes (FITC-WGA); blue: cell nuclei (DAPI); red: polyplexes (Cy3-siRNA).

This qualitative observation with CLSM was quantified by analyzing the weighted number of nanoparticles in the cells by pixel analysis of the CLSM images as

described by Labouta et al. [35]. The advantage of this method, over manual counting of the number of fluorescent spots, is that it avoids human errors and also considers the area of the fluorescent spots which are larger than the resolution limit. For the inhibitors CHL and NYS we found predominant internalization of the nanoparticles (85 % and 81 %, respectively) while for EIPA only a very small uptake (6 %) was observed within an incubation time of 4 h.

To investigate the precise interaction of polyplexes with the lung epithelial cells, one representative single polyplex particle ($N/P = 2$) was tracked during its uptake into the cell and its passage through the early endosome which was selectively stained. The polyplex was detected using two independent channels, making use of the two distinct fluorescence bands of Cy3 linked to siRNA and Atto647N conjugated to the cationic **PRx2**. Co-localization of both fluorescence signals clearly demonstrated that the polyrotaxane is transporting the siRNA into the cell. The uptake into the cell took about 10 min. After a longer time (1 h) the Cy3 fluorescence of the polyplex was nearly extinguished, while the fluorescence of Atto647N still remained. This observation was attributed to the weaker binding siRNA within the polyplex in comparison to pDNA, as already observed with fluorescence correlation spectroscopy. siRNA appeared to fade out of the polyplexes still leaving them intact.

a)

b)

Figure 7. Tracking of a single nanoparticle ($N/P = 2$), following the fluorescence of a) Atto647 (excitation 633 nm, emission 650-710 nm) and b) Cy3 (excitation 543 nm, emission 560-615 nm), during the migration through the cytosome stained in green, after 185, 195, 230, 255 min.

Nevertheless, the siRNA transported and released in the A549 cells was found to be biologically active. Knockdown efficiencies for the luciferase gene of 60 % and 45 % were found for $N/P = 2$ and $N/P = 1$, respectively. The lower value for $N/P = 1$ might be due to lower uptake of polyplexes, and hence the associated siRNA, into the cells due to their overall negative charge.

Figure 8. Luciferase gene silencing in A549 cells by anti-Luc siRNA (100 pmol), its cationic PRx polyplex, its anionic PRx polyplex and its complex with jetPrime™.

4. Conclusion

Polyrotaxanes, assembled by subsequent threading of the heptacationic β -CD derivative **HAES β CD** and α CD onto ionenes, are promising carriers for transfection of siRNA into mammalian cells, because their limited lifetime allows a timely release within the cell. Fluorescent labeling of siRNA allows to follow its uptake into the polyplexes by fluorescence correlation spectroscopy and to track its journey within the nanoparticles into the cell by confocal fluorescence microscopy. Knockdown efficiency might be further improved by optimization of the dose, the structure and the composition of the polyplexes. Furthermore PEGylation or attachment of lipids might be advantageous as already known for PEI [39, 40] and polyamidoamines [9].

5. Acknowledgments

Dr. Prajakta Dandekar was the recipient of a European Respiratory Society / Marie Curie Joint Research Fellowship - Number MC [1634]-2010. This research received funding from the European Respiratory Society and the European Community's Seventh Framework Programme FP7/2007-2013 - Marie Curie Actions under grant agreement RESPIRE, PCOFUND-GA-2008-229571.

6. References

- [1] S. Teramoto, T. Ishii, T. Matsuse, Crisis of adenoviruses in human gene therapy. *The Lancet* 355(9218) (2000) 1911-1912.
- [2] J.M. Wilson, Lessons learned from the gene therapy trial for ornithine transcarbamylase deficiency. *Mol. Genet. Metab.* 96(4) (2009) 151-157.
- [3] O. Boussif, F. Lezoualch, M.A. Zanta, M.D. Mergny, D. Scherman, B. Demeneix, J.P. Behr, A versatile vector for gene and oligonucleotide transfer into cells in culture and in vivo: Polyethylenimine. *Proc. Natl. Acad. Sci. U. S. A.* 92(16) (1995) 7297-7301.
- [4] C.L. Gebhart, A.V. Kabanov, Evaluation of polyplexes as gene transfer agents. *J. Controlled Release* 73(2-3) (2001) 401-416.
- [5] S. Mansouri, P. Lavigne, K. Corsi, M. Benderdour, E. Beaumont, J.C. Fernandes, Chitosan-DNA nanoparticles as non-viral vectors in gene therapy:

- strategies to improve transfection efficacy. *Eur. J. Pharm. Biopharm.* 57(1) (2004) 1-8.
- [6] S. Taetz, N. Nafee, J. Beisner, K. Piotrowska, C. Baldes, T.E. Murdter, H. Huwer, M. Schneider, U.F. Schaefer, U. Klotz, C.M. Lehr, The influence of chitosan content in cationic chitosan/PLGA nanoparticles on the delivery efficiency of antisense 2-O-methyl-RNA directed against telomerase in lung cancer cells. *Eur. J. Pharm. Biopharm.* 72(2) (2009) 358-369.
- [7] W. Zauner, M. Ogris, E. Wagner, Polylysine-based transfection systems utilizing receptor-mediated delivery. *Adv. Drug Delivery Rev.* 30(1-3) (1998) 97-113.
- [8] S. Hossain, A. Stanislaus, M.J. Chua, S. Tada, Y.I. Tagawa, E.H. Chowdhury, T. Akaike, Carbonate apatite-facilitated intracellularly delivered siRNA for efficient knockdown of functional genes. *J. Controlled Release* 147(1) (2010) 101-108.
- [9] T. Fröhlich, D. Edinger, R. Kläger, C. Troiber, E. Salcher, N. Badgujar, I. Martin, D. Schaffert, A. Cengizeroglu, P. Hadwiger, H.-P. Vornlocher, E. Wagner, Structure-activity relationships of siRNA carriers based on sequence-defined oligo (ethane amino) amides. *J. Controlled Release* 160 (2012) 532-541.
- [10] J. Chen, C. Wu, D. Oupicky, Bioreducible Hyperbranched Poly(amido amine)s for Gene Delivery. *Biomacromolecules* 10(10) (2009) 2921-2927.
- [11] L. Gudmundsdotter, B. Wahren, B.K. Haller, A. Boberg, U. Edbäck, D. Bernasconi, S. Buttò, H. Gaines, N. Imami, F. Gotch, F. Lori, J. Lisziewicz, E. Sandström, B. Hejdeman, Amplified antigen-specific immune responses in HIV-1 infected individuals in a double blind DNA immunization and therapy interruption trial. *Vaccine* 29(33) (2011) 5558-5566.
- [12] A.A. Sidi, P. Ohana, S. Benjamin, M. Shalev, J.H. Ransom, D. Lamm, A. Hochberg, I. Leibovitch, Phase I/II Marker Lesion Study of Intravesical BC-819 DNA Plasmid in H19 Over Expressing Superficial Bladder Cancer Refractory to Bacillus Calmette-Guerin. *The Journal of Urology* 180(6) (2008) 2379-2383.
- [13] M.E. Davis, The First Targeted Delivery of siRNA in Humans via a Self-Assembling, Cyclodextrin Polymer-Based Nanoparticle: From Concept to Clinic. *Mol. Pharm.* 6(3) (2009) 659-668.
- [14] N.D. Weber, O.M. Merkel, T. Kissel, M.A. Muñoz-Fernández, PEGylated poly(ethylene imine) copolymer-delivered siRNA inhibits HIV replication in vitro. *J. Controlled Release*(157) (2011) 55-63.
- [15] S. Mao, M. Neu, O. Germershaus, O. Merkel, J. Sitterberg, U. Bakowsky, T. Kissel, Influence of polyethylene glycol chain length on the physicochemical and biological properties of poly(ethylene imine)-graft-poly(ethylene glycol) block copolymer/SiRNA polyplexes. *Bioconjugate Chem.* 17(5) (2006) 1209-1218.
- [16] M.E. Davis, J.E. Zuckerman, C.H.J. Choi, D. Seligson, A. Tolcher, C.A. Alabi, Y. Yen, J.D. Heidel, A. Ribas, Evidence of RNAi in humans from systemically administered siRNA via targeted nanoparticles. *Nature* 464(7291) (2010) 1067-1070.
- [17] M. Wiese, H.P. Cordes, H. Chi, J.K. Seydel, T. Backensfeld, B.W. Müller, Interaction of prostaglandin E1, with α -cyclodextrin in aqueous systems: Stability of the inclusion complex. *J. Pharm. Sci.* 80(2) (1991) 153-156.

- [18] G. Wenz, An Overview of Host-Guest Chemistry and its Application to Nonsteroidal Anti-Inflammatory Drugs. *Clin. Drug Invest.* 19, Suppl. 2 (2000) 21-25.
- [19] M. Abdel-Tawab, H. Zettl, M. Schubert-Zsilavecz, Nonsteroidal Anti-Inflammatory Drugs: A Critical Review on Current Concepts Applied to Reduce Gastrointestinal Toxicity. *Curr. Med. Chem.* 16(16) (2009) 2042-2063.
- [20] F. Leroy-Lechat, D. Wouessidjewe, J.-P. Andreux, D. Duchene, F. Puisieux, Evaluation of the cytotoxicity of cyclodextrins and hydroxypropylated derivatives. *Int. J. Pharm.* 101 (1994) 97-103.
- [21] A. Steffen, C. Thiele, S. Tietze, C. Strassnig, A. Kämper, T. Lengauer, G. Wenz, J. Apostolakis, Improved cyclodextrin based receptors for camptothecin by inverse virtual screening. *Chem.--Eur. J.* 13 (2007) 6801–6809.
- [22] G. Wenz, C. Strassnig, C. Thiele, A. Engelke, B. Morgenstern, K. Hegetschweiler, Recognition of ionic guests by ionic beta-cyclodextrin derivatives. *Chem.--Eur. J.* 14(24) (2008) 7202-7211.
- [23] C. Thiele, D. Auerbach, G. Jung, G. Wenz, Inclusion of chemotherapeutic agents in substituted beta-cyclodextrin derivatives. *J. Inclusion Phenom. Macrocyclic Chem.* 69(3-4) (2011) 303-307.
- [24] A. Harada, J. Li, M. Kamachi, The molecular necklace: a rotaxane containing many threaded α -cyclodextrins. *Nature* 356 (1992) 325-327.
- [25] T. Ooya, H.S. Choi, A. Yamashita, N. Yui, Y. Sugaya, A. Kano, A. Maruyama, H. Akita, R. Ito, K. Kogure, H. Harashima, Biocleavable polyrotaxane - Plasmid DNA polyplex for enhanced gene delivery. *J. Am. Chem. Soc.* 128(12) (2006) 3852-3853.
- [26] A. Yamashita, D. Kanda, R. Katoono, N. Yui, T. Ooya, A. Maruyama, H. Akita, K. Kogure, H. Harashima, Supramolecular control of polyplex dissociation and cell transfection: Efficacy of amino groups and threading cyclodextrins in biocleavable polyrotaxanes. *J. Controlled Release* 131(2) (2008) 137-144.
- [27] W. Herrmann, B. Keller, G. Wenz, Kinetics and thermodynamics of the inclusion of ionene-6, 10 in α -cyclodextrin in an aqueous solution. *Macromolecules* 30 (1997) 4966-4972.
- [28] G. Wenz, C. Gruber, B. Keller, C. Schilli, T. Albuzat, A. Mueller, Kinetics of Threading α -Cyclodextrin onto Cationic and Zwitterionic Poly(bola-amphiphiles). *Macromolecules* 39(23) (2006) 8021-8026.
- [29] T. Albuzat, M. Keil, J. Ellis, C. Alexander, G. Wenz, Transfection of luciferase DNA into various cells by cationic cyclodextrin polyrotaxanes derived from ionene-11. *J. Mater. Chem.* 22(17) (2012) 8558 - 8565.
- [30] D. Rohan, K. Mahesh, R. Manoj, M. Sekhar, Inhibition of bfl-1/A1 by siRNA inhibits mycobacterial growth in THP-1 cells by enhancing phagosomal acidification. *Biochimica et Biophysica Acta - General Subjects* 1780(4) (2008) 733-742.
- [31] G. Wenz, I. Kräuter, E. Sackmann, Assembly of a fluorescent cyclodextrin polyrotaxane and its detection by fluorescence microscopy. *J. Polym. Sci., Part A: Polym. Chem.* 47(22) (2009) 6223-6230.

- [32] B. Hinkeldey, A. Schmitt, G. Jung, Comparative Photostability Studies of BODIPY and Fluorescein Dyes by Using Fluorescence Correlation Spectroscopy. *ChemPhysChem* 9(14) (2008) 2019-2027.
- [33] R. Rigler, Ü. Mets, J. Widengren, P. Kask, Fluorescence correlation spectroscopy with high count rate and low background: analysis of translational diffusion. *European Biophysics Journal* 22(3) (1993) 169-175.
- [34] D.S. Banks, C. Fradin, Anomalous diffusion of proteins due to molecular crowding. *Biophys. J.* 89(5) (2005) 2960-2971.
- [35] H.I. Labouta, T. Kraus, L.K. El-Khordagui, M. Schneider, Combined multiphoton imaging-pixel analysis for semiquantitation of skin penetration of gold nanoparticles. *Int. J. Pharm.* 413(1-2) (2011) 279-282.
- [36] A.I. Ivanov, in: J. M. Walker (Ed.), *Methods in Molecular Biology*, Vol. 440, Humana Press, 2008, pp. 15-33.
- [37] S. Grosse, Y. Aron, G. Thévenot, D. Francois, M. Monsigny, I. Fajac, Potocytosis and cellular exit of complexes as cellular pathways for gene delivery by polycations. *J. Gene Med.* 7(10) (2005) 1275-1286.
- [38] X. Banquy, F. Suarez, A. Argaw, J.-M. Rabanel, P. Grutter, J.-F. Bouchard, P. Hildgen, S. Giasson, Effect of mechanical properties of hydrogel nanoparticles on macrophage cell uptake. *Soft Matter* 5(20) (2009) 3984-3991.
- [39] A. Alshamsan, A. Haddadi, V. Incani, J. Samuel, A. Lavasanifar, H. Uludag, Formulation and Delivery of siRNA by Oleic Acid and Stearic Acid Modified Polyethylenimine. *Mol. Pharm.* 6(1) (2008) 121-133.
- [40] T. Merdan, K. Kunath, H. Petersen, U. Bakowsky, K.H. Voigt, J. Kopecek, T. Kissel, PEGylation of Poly(ethylene imine) Affects Stability of Complexes with Plasmid DNA under in Vivo Conditions in a Dose-Dependent Manner after Intravenous Injection into Mice. *Bioconjugate Chem.* 16(4) (2005) 785-792.