

Supplementary Material

Dissolution techniques for in vitro testing of dry powders for inhalation

Sabine May¹, Birte Jensen², Markus Wolkenhauer², Marc Schneider^{1,3}, Claus Michael Lehr^{1,3,4}

¹ PharmBioTec GmbH, Saarbrücken, Germany

² Boehringer Ingelheim Pharma GmbH & Co KG, Ingelheim, Germany

³ Biopharmaceutics and Pharmaceutical Technology, Saarland University, Saarbrücken, Germany

⁴ Helmholtz Institute for Pharmaceutical Research Saarland (HIPS), Helmholtz Center for Infection Research (HZI), Saarbrücken, Germany




Figure S1: DSC of substance A amorphous base: glass transition point is between 6 and 10 minutes at approx. 110°C (heating rate 10°C/min)

Measurements were performed on a DSC 820 from Mettler Toledo (Gießen, Germany)